



## Technical Data Sheet

# SILASTIC™ RTV-4133-M2 Liquid Silicone Rubber Base

RTV silicone rubber for use when fast demold time is critical

### Features & Benefits

- Fast RTV cure; heat accelerable
- Very high inhibition resistance
- Very low shrinkage
- High durometer hardness
- Good tear strength and elasticity

### Composition

- Two-part, pourable liquid RTV silicone rubber
- Base: beige
- Curing agent: regal blue

### Applications

- Prototype design
- Production tooling
- Artistic and renovation applications
- Architectural and furniture components

### Typical Properties

Specification Writers: These values are not intended for use in preparing specifications.

Property	Unit	Result
<b>As Supplied</b>		
Base Color		Beige
Viscosity	poise	1150
Curing Agent Color		Regal Blue
<b>As Mixed – 100 Parts Base to 10 Parts Curing Agent by Weight</b>		
Viscosity	poise	660
Specific Gravity		1.29
<b>As Cured<sup>1</sup></b>		
Durometer Hardness, Shore A	points	59
Tensile Strength	MPa (psi)	4.8 (700)
Elongation	percent	200
Die B Tear Strength	kN/m (ppi)	15 (85)
Linear Shrink	percent	< 0.1

1. Cured 24 hours at 25°C (77°F)

## Description

SILASTIC™ RTV-4133-M2 Liquid Silicone Rubber Base is a more inhibition-resistant, faster curing version of SILASTIC™ M-2 RTV Silicone Rubber developed specifically for use when faster demold time is critical. At room temperature, SILASTIC RTV-4133-M2 Liquid Silicone Rubber Base provides 1½ hours of working time, yet is able to be demolded in four to five hours.

This two-part material is designed for detailed reproduction of surfaces and objects used in prototype design and production tooling, artistic and renovation applications, and architectural and furniture components made with urethane foams and other resins.

SILASTIC RTV-4133-M2 Liquid Silicone Rubber Base is beige, and its curing agent is regal blue to aid inspection for uniform blending. An easy-to-mix ratio of 10:1 base to curing agent helps ensure accurate measuring and blending by hand or machine. The material cures by an addition reaction at room or elevated temperatures, and can be molded in unlimited thickness – regardless of part configuration or degree of confinement.

## How To Use

### Pattern Preparation

Certain contaminants found in mold-making operations can prevent SILASTIC RTV-4133-M2 Liquid Silicone Rubber Base from curing. Patterns to be molded should be thoroughly cleaned to remove grease, oil, and other surface contaminants. Care should also be taken to ensure that corners, crevices, and draws are free of dirt or particles of foreign matter. A light “blow over” with compressed air is advised when the pattern has convoluted draws or undercuts. Then, the original model or pattern should be placed in a light frame or cardboard, foil, wood, or other material. There should be approximately (0.95-cm) 3/8- inch clearance on all sides and over the top of the pattern. The pattern should be attached securely to the bottom of the frame so it does not float.

A pattern release agent should then be wiped or sprayed on the pattern. Spreading a light coat of release agent on the sides and underside of the top of the frame will facilitate release.

A good pattern release agent can be made by combining five percent petroleum jelly and 95 percent solvent.<sup>1</sup> Combine the materials and let stand overnight – then shake by hand to provide a good mix.

### Application

Weigh out 100 parts of SILASTIC RTV-4133-M2 Liquid Silicone Rubber Base and 10 parts of curing agent in a clean container. Mix until the curing agent is completely dispersed in the base and a uniform color is obtained.

Entrapped air should be removed in a vacuum chamber, allowing the mixture to completely expand and then collapse.

After an additional three minutes of vacuum, the mix should be inspected and can be used if free of air bubbles. A volume increase of three to four times will occur on vacuum deairing of the mixture, so a suitably large container should be chosen.

1. When handling solvents, always provide adequate ventilation. Keep away from heat, sparks and open flames. Always follow all precautions given on the solvent container label, and ensure compliance with local, state and federal regulations.

## How To Use (Cont.)

Pressure casting may be substituted with equal success. Pour the mixed base and curing agent onto the master, avoiding air entrapment.

The catalyzed mixture will typically cure to a flexible rubber within four to five hours at room temperature, at which time the part can be demolded. Heat accelerating the cure is possible, but some physical property changes, such as increased durometer hardness, will occur.

NOTE: Above room temperature, the working time for SILASTIC RTV-4133-M2 Liquid Silicone Rubber Base is substantially decreased. Due to this decrease in working time, automatic dispensing equipment is recommended.

### **Inhibition of Cure**

All addition cure silicone elastomers are susceptible to cure inhibition when in contact with certain materials and chemicals. It is strongly recommended that mixing containers, mold construction materials, masters, and release agents be checked for any inhibition effect before use by properly mixing SILASTIC RTV-4133-M2 Liquid Silicone Rubber Base and curing agent and applying a small amount against the surfaces. Inhibition has occurred if the elastomer is only partially cured after 16 hours, or has a sticky surface in contact with another material. Amines and sulfur-containing materials are strong inhibitors, as are organotin salts used in condensation cure RTV silicones. Wet or moist surfaces can cause gas bubbles to form during cure in the silicone adjacent to the substrate surface.

## Handling Precautions

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ PRODUCT AND SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION. THE SAFETY DATA SHEET IS AVAILABLE ON THE DOW WEBSITE AT [WWW.CONSUMER.DOW.COM](http://WWW.CONSUMER.DOW.COM), OR FROM YOUR DOW SALES APPLICATION ENGINEER, OR DISTRIBUTOR, OR BY CALLING DOW CUSTOMER SERVICE.

## Usable Life And Storage

Product should be stored at or below 32°C (90°F) in original, unopened containers.

Both base and curing agent can be sensitive to moisture and contamination. Ensure containers are tightly closed after use.

## Limitations

This product is neither tested nor represented as suitable for medical or pharmaceutical uses.

Not intended for human injection. Not intended for food use.

## Health And Environmental Information

To support customers in their product safety needs, Dow has an extensive Product Stewardship organization and a team of product safety and regulatory compliance specialists available in each area.

For further information, please see our website, [www.consumer.dow.com](http://www.consumer.dow.com) or consult your local Dow representative.

UNRESTRICTED – May be shared with anyone

®™ Trademark of The Dow Chemical Company ("Dow") or an affiliated company of Dow

SILASTIC™ RTV-4133-M2 Liquid Silicone Rubber Base

© 2017 The Dow Chemical Company. All rights reserved.

<http://www.silastic.com>

**LIMITED WARRANTY INFORMATION – PLEASE READ CAREFULLY**

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that our products are safe, effective, and fully satisfactory for the intended end use. Suggestions of use shall not be taken as inducements to infringe any patent.

Dow's sole warranty is that our products will meet the sales specifications in effect at the time of shipment.

Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted.

**TO THE FULLEST EXTENT PERMITTED BY APPLICABLE LAW, DOW SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY.**

**DOW DISCLAIMS LIABILITY FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES.**

